



COMPOSITION

Moulded friction material, composed of rubber, synthetic resins, friction fibres and mineral filled, with the necessary vulcanised agents. It does not contains asbestos neither cadmium.
According to RoSH

LOOK

Colour: dark crimson
Surface quality: peened

PHISICAL-CHEMICAL PROPIERTIES

Hardness	97 ± 5 SHORE "C"
Specific weight	1,95 ± 0,05 gr./cm ³
Volatile	> 0 y < 3% in weight
Solvents extraction	6% max.

EFFICIENCY

Maximum working pressure	10 Kg. / cm ²
Maximum working temperature	300°C intermittent working 200°C continuos working
Static friction coefficient	0.20 < μ < 0.28

SUGGESTIONS

Industrial brakes.
Automobile, motorbike brakes.

SPECIAL

Hardness and mechanical proprieties improved.
Excellent response for fading and very quick recovery

PRESENTATION

It can be as:

- Integral moulded.
- Mixed moulded.
- Friction bands.

FIRST DATE: JULY, 10th/1992

LAST REVISION: OCTOBER 2004